

## Demineralization Resin

### Weak Base Anion (Macroporous)

**DOSHION AWB 7050 D UPS** resin is a uniform particle size Macroporous Weakly Base Anion Exchange Resin with high capacity. It is based on a Styrene-divinylbenzene co-polymer matrix. It is specifically designed to give high throughput and economical operation in both water and non water applications.


#### Outstanding Characteristics of AWB 7050 D UPS :

- Exceptional physical, chemical and thermal stability under varied influent conditions.
- Excellent resin kinetics leading to higher throughput.
- Effective adsorption of organic and there removal, hence making it suitable for organic removal/scavenging.

Properties	
Matrix	Cross Linked Polystyrene Macroporous
Functional group	Tertiary Amine
Ionic Form	Free Base
Physical Form	Moist Strong Beads
Particle Size (mm)	0.5-0.6 (mean)
Moisture Content %	50-63
Total exchange capacity eq/ltr (min.)	1.3
Bulk Density or Shipping Weight gms/ ltr	670-720
Solubility in common solvents	Insoluble
Volume Change %(Max): FB to HCL	20
Uniformity Coefficient	1.3 to 1.4

Operating Conditions		
Operating pH range		1-9
Operating temperature	°C (max)	40
Minimum bed depth	mm	750
Regenerant Concentration	%	2-4 (NaOH)
Regenerant flow rate	*BV/hr	4-6
Regenerant contact time	Minutes	30 min
Displacement Rinse rate	*BV/hr	15-25
Service flow rate	*BV/hr	10-45

\* Bed Volume



## Full Range of Ion Exchange Resins

Cation Exchange Resin	Anion Exchange Resin	Speciality Resin	DM Resin
CSA 121	GA 11	DCHR 74	DMB 13
CSA 9	GA 12	DCHR 78	
CSA 9 L	GA 13	DIRM 412	
CSA 29	ASB 108	DCR 11	
CSA 609 D	ASB 171	CWS 66 D	
CWA 63	ASB 1080 D UPS	DMB 13 S	
CWA 92 D	ASB 8020 D	CGC 1200	
CSA 309	AWB 7020 D	CMC 1900	
	AWB 7030 D	CMC 2400	
	AWB 7050 D		
	GA 711		

## Full Range of Membrane Performance Chemical

RO Membrane Chemicals	UF Membrane Chemicals	EDI Membrane Chemicals	Speciality Chemicals
DCC – Bior	DCC - UFC - I	EDC - SNO - IO - 56	Doshion - 1180
DCC – Inor	DCC - UFC - O	EDC - SNO - IO - 74	Doshion - C 8100
DCC - Col	DCC - UFC - C		Doshion - 3426
DCC - Stor	DCC - UFC - S		Doshion - 9711 (P)
Doshion - 51 (HS)			Doshion - 9718 (Z)
Doshion - 52 (L)			
Doshion - 53			
DoScale - 65			
Doshion - 6311 - LS			

## Full Range of Pharmaceutical Polymers

Active Pharma Ingredients	Excipients	Speciality Polymers	Ready Mix & Ready to Use
Doshion P-504 (Sodium Polystyrene Sulphonate USP / EP)	Doshion P-504 (Polystyrene Resin)	Doshion P-520	Doshion P-542 AB (R)
Doshion P-548 BP (Calcium Polystyrene Sulphonate BP)	Doshion P-514	Doshion P-535	Azithromycin Taste Masked (7.5%)
Doshion P-548 JP (Calcium Polystyrene Sulphonate JP)	Doshion P-542		
Doshion P-550 (Cholestyramine Resin USP / EP)	Doshion P-542 AB		
	Doshion P-542 CP		
	Doshion P-542 D		
	Doshion P-544 C		
	Doshion P-544 R		
	Polyflash Doshion P-544 DS		
	Doshion P-544 DS (Cipro)		
	Polyflash Doshion P-544 DB		
	Polyflash Doshion P-544 D		
	Doshion P-550		
	Doshion P-551 (Polyacrilix Resin)		

**doshion**<sup>®</sup>  
Translating Source Into Resource

**Doshion Poly Science Pvt. Ltd.**

Building Number: 9 – 10, Sigma Corporates,  
Off. Sindhu Bhavan Road, Ahmedabad – 380054, Gujarat, India

+91 079 – 4800 7766 | [polymers@doshion.com](mailto:polymers@doshion.com) | [www.doshionpoly.com](http://www.doshionpoly.com)

