

## Taste Masking

Methacrylic co-Polymer with divinyl benzene

### Principal Application:

- Taste masking of bitter drugs

Typical Physical & Chemical Characteristics	
Polymer Structure	Weak Acid Cation Exchange Resin
Appearance / Physical Form	White to off-white Powder
Functional Group	-COO-
Matrix	Methacrylic
Ionic Form	K <sup>+</sup>
pH	9.5 to 10.5
Potassium Content	24 to 28 %
Sodium Content	< 0.2 %
Iron Content	< 100 ppm
Arsenic Content	< 3 ppm
Moisture Content	< 10 % w/w
Particle size: Retain over 100 BS	< 1 %
Retain over 200 BS	< 30 %

### Packaging:

10 kg and 25 kg Fibre Drum

### Documents Available:

CEP, DMF



## Full Range of Pharmaceutical Polymers

Speciality Polymers	Active Pharmaceutical Ingredients	Ready Mix & Ready to Use
<b>P-520</b> (Vitamin C Purification)	<b>P-548</b> (Calcium Polystyrene Sulfonate BP/ JP)	<b>P-542 AB (R)</b>
<b>P-535</b> (Separation of Aminoacids, Enzymes & Alkloids)	<b>P-504</b> (Sodium Polystyrene Sulfonate USP/ EP)	Azithromycin Taste Masked (7.5%)
<b>P-545 8X</b> (Dextromethorphan Polistirex Manufacturing)	<b>P-550</b> (Cholestyramine Resin USP / EP)	

  

Taste Masking	Tablet Disintegration	Control / Sustained Release
<b>P-551</b> (Polacrilex Resin USP)	<b>P-544 DS</b> (Polacrillin Potassium USP)	<b>P-504</b> (Sodium Polystyrene Sulfonate)
<b>P-514</b> (Methacrylic Acid Polymer with Divinyl Benzene & Acrylic Acid)	<b>P-544 D</b> (Polacrillin Potassium USP)	<b>P-550</b> (Cholestyramine)
<b>P-542</b> (Methacrylic Acid Polymer with Divinyl Benzene & Acrylic Acid)	<b>P-544 DB</b> (Polacrillin Potassium)	
<b>P-542 AB</b> (Methacrylic Acid Polymer with Divinyl Benzene & Acrylic Acid)		
<b>P-542 CP</b> (Methacrylic Acid Polymer with Divinyl Benzene & Acrylic Acid)		
<b>P-542 D</b> (Methacrylic Acid Polymer with Divinyl Benzene & Acrylic Acid)		
<b>P-544 R</b> (Methacrylic co-Polymer with divinyl benzene)		
<b>P-544 DS Cipro</b> (Potassium Salt of Weak Acid Cation Resin)		
<b>P-544 C</b> (Methacrylic acid Polymer with Divinyl Benzene and Acrylic acid, Potassium Salt)		



**doshion**<sup>®</sup>  
Translating Source Into Resource

**Doshion Poly Science Pvt. Ltd.**

Building Number: 9 – 10, Sigma Corporates,  
Off. Sindhu Bhavan Road, Ahmedabad – 380054, Gujarat, India

+91 079 – 4800 7766 | [polymers@doshion.com](mailto:polymers@doshion.com) | [www.doshionpoly.com](http://www.doshionpoly.com)

